



C.I.F

DATA SHEET

FR4

200706

IEC Specification		
IEC Specification	IPC-4101/21	UL/ANSI Grade FR-4 (type L21)
DESCRIPTION		
Glass epoxy. Rigid Laminates - PTH applications, supports standard double side lead free assembly processes.		
Reinforcement: Woven E-glass	Flame Retardant: Bromine Rohs compl.	Filler: Non
Glass Transition T_g: 135°C	Resin system (primary): Difunctional epoxy	
ROHS Compliance directive 2002/95/EC		
CERTIFICATIONS AND HOMOLOGATIONS	UL	E 47820

PROPERTIES (Cu 35um, thickness 1.6mm)	IPC 4101 Paragraph	IPC TM-650 Method	Laminate < 0.50mm		Laminate ≥ 50mm	
			Specification	Typical values	Specification	Typical values
SURFACE QUALITY ⁽¹⁾	3.8.3	2.1.5	Grade A	Grade A	Grade A	Grade A
THICKNESS ⁽¹⁾	3.8.4.2	2.2.18	Class L	Class L	Class L	Class L
PEEL STRENGTH (std Cu foil)						
After thermal stress, 10" 288°C	3.9.1.1.1	2.4.8	1.5 N/mm	1.8 N/mm	1.4 N/mm	1.8 N/mm
At 125°C	3.9.1.1.2	2.4.8 / 2 / 3	1.3 N/mm	1.6 N/mm	1.3 N/mm	1.6 N/mm
After process solutions	3.9.1.1.3	2.4.8	1.3 N/mm	1.8 N/mm	1.3 N/mm	1.8 N/mm
VOLUME RESISTIVITY	3.11.1.3	2.5.17.1				
90% HR / 35 / 96h			10 ⁸ MΩ·cm	10 ⁸ MΩ·cm	n/a	n/a
After moisture			n/a	n/a	10 ⁴ MΩ·cm	10 ⁷ MΩ·cm
At elevated temp (E 24h / 125°C)			10 ⁷ MΩ·cm	10 ⁷ MΩ·cm	10 ⁷ MΩ·cm	10 ⁷ MΩ·cm
SURFACE RESISTIVITY	3.11.1.4	2.5.17.1				
90% HR / 35 / 96h			10 ⁶ MΩ·cm	10 ⁷ MΩ·cm	n/a	n/a
After moisture			n/a	n/a	10 ⁴ MΩ	10 ⁶ MΩ
At elevated temp (E 24h / 125°C)			10 ⁵ MΩ·cm	10 ⁵ MΩ·cm	10 ⁵ MΩ·cm	10 ⁵ MΩ·cm
MOISTURE ABSORTION	3.12.1.1	2.6.2.1	n/a	n/a	0.35%	0.19 %
DIELECTRIC BREAKDOWN	3.11.1.6	2.5.6	n/a	n/a	42 kV	
PERMITIVITY at 1MHz ⁽²⁾	3.11.1.1	2.5.5	4.8	4.8	4.8	4.8
LOSS TANGENT at 1MHz	3.11.1.2	2.5.5	2.027	2.027	0.027	0.027
FLEXURAL STRENGTH	3.9.1.3	2.4.4				
Length direction			n/a	n/a	415 N/mm ²	550 N/mm ²
Cross direction			n/a	n/a	345 N/mm ²	450 N/mm ²
ARC RESISTANCE	3.11.1.5	2.5.1	60 sec	120 sec	60 sec	120 sec
THERMAL STRESS (10" at 288°C)	3.10.1.2	2.4.13.1	Pass visual	60 sec	Pass visual	60 sec
ELECTRIC STRENGTH ⁽²⁾	3.11.1.7	2.5.6.2	32kV/mm	36kV/mm	n/a	n/a
FLAMMABILITY	3.10.1.1	UL 94	V - 0	V - 0	V - 0	V - 0
GLASS TRANSITION TEMP (T _g)	3.10.1.6	2.4.25 DSC	n/a	n/a	130°C	135°C
DIMENSIONAL STABILITY ⁽¹⁾	3.9.12	2.4.39	-	-	± 200ppms	± 100ppms
COMPARATIVE TRACKING INDEX-CTI	IEC60112	-	-	-	200 V	230 V

AVAILABILITY

STANDARD SHEETS SIZES				Logo (red) IGAV
927 x 1232 mm and 1082 x 1232 mm		Tolerance +13/-0mm		
Also available in cut panels to customer requirement				
SQUARENESS		3 mm max., as differential between diagonal measurement		
Copper thickness		18, 35 and 70 mic (other copper thickness upon request)		

Specification column corresponds to guaranteed values. Typical values are average values of current production and are based on reliable analytical methods, they have to be used only as guideline and not give rise to any rights under warranty terms. Aismalibar reserves the right to future changes.

Notes: ⁽¹⁾ Other level upon agreement
⁽²⁾ Influenced by build-up (% of resin)
⁽³⁾ As agreed upon between user and supplier

IEC Specifications (IEC 61249-2-7) and Test Methods (IEC 61189-2): IEC specifications and test methods are in most of cases equivalent to IPC standards. They can be used as reference upon specific agreement between customer and supplier.

