

## Technical data



**Material** : Polyvinylchloride (hard PVC)

**Colour** : grey RAL 7030

**Operating temperature** : -5 °C to +65 °C

|                                | Typical values           | Test method |
|--------------------------------|--------------------------|-------------|
| <b>Density</b>                 | : 1.55 g/cm <sup>3</sup> | DIN 53479   |
| <b>Flammability</b>            | : self-extinguishing V0  | UL 94       |
| <b>Formaldehyde</b>            | : not included           |             |
| <b>Cadmium</b>                 | : not included           |             |
| <b>Dielectric conductivity</b> | : 3.2 - 4.0              | AST D150    |
| <b>Dielectric strength</b>     | : 70 kV/mm               | IEC 243     |
| <b>Resistance</b>              | : 10 <sup>13</sup> Ohm   | IEC 93      |
| <b>Specification</b>           | : UL                     |             |

**HellermannTyton**

HellermannTyton GmbH  
Grosser Moorweg 45  
D-25436 Tornesch

Telefon: +49 (0) 4122/701-1  
Telefax: +49 (0) 4122/701-400

This information is based on our experience and does not imply suitability without prior testing. Due to the variables of manufacture and environmental conditions it is strongly recommended that samples are tested in-situ.

PM-nb.V01.0/04.02.2010