

TECHNICAL DATA SHEET

ECO 5 Sn99-Cu0.7Ag0.3 Solder alloy



UNIVERSITAT DE
BARCELONA

ECO 5 Sn99Cu0.7Ag0.3. Tin-Silver-Copper solder according to EN-ISO 9453, alloy 501

TECHNICAL DATA – ECO 5

Melting point (°C)	221/227
Density at 20°C (gcm⁻³)	7.33
Tensile strength (MPa)	29.4
Elongation (%)	22 (figure 1a)
Hardness (HB)	14

*All the characterizations and procedures done to obtain the physical properties of the solder were carried out in collaboration with the University of Barcelona.

GENERAL INFORMATION

ECO 5 is a high performance lead-free tin-copper-silver solder alloy (figure 1b) that shows better fluidity compared to silver-free alloys. The composition of this solder complies with the ISO 9453:2015 standards and RoHS directive. This makes the ECO 5 suitable for a wide variety of applications in which lead is prohibitive. This solder can be used in wave, selective, hand and SMT reflow soldering.




Figure 1. a) Stress-Strain curve and b) SEM image for ECO 5 solder.

Revision date: 18/03/2020

TECHNICAL DATA SHEET

ECO 5 Sn99-Cu0.7Ag0.3 Solder alloy

CUSTOMER ADDED VALUE

- Excellent wetting and fluidity.
- Excellent solderability due to fast wetting.
- Low bridging levels.
- Excellent performance and compatibility across a wide range of flux technologies.
- Low cost compared to other high-silver containing alloys.

COMPATIBILITY AND CLEANING

This ECO 5 alloy is compatible with a wide variety of flux types that we also offer in our catalogue. For more information ask us for the corresponding technical data sheet.

ALLOY COMPOSITION (Sn99Cu0.7Ag0.3)

COMPOSITION	
Tin (Sn)	Rem.
Copper (Cu)	0,5-0,9
Silver (Ag)	0,2-0,4
MAXIMUM IMPURITY LEVELS ACCORDING TO ISO 9453:2015	
Antimony (Sb)	0,10
Bismuth (Bi)	0,06
Gold (Au)	0,05
Lead (Pb)	0,07
Indium (In)	0,10
Aluminum (Al)	0,001
Arsenic (As)	0,03
Cadmium (Cd)	0,002
Iron (Fe)	0,02
Nickel (Ni)	0,01
Zinc (Zn)	0,001

Revision date: 18/03/2020



UNIVERSITAT DE
BARCELONA

TECHNICAL DATA SHEET

ECO 5 Sn99-Cu0.7Ag0.3 Solder alloy

STORAGE AND HANDLING

To avoid any undesirable damage, please follow these advices:

- Do not fire anything near storage area.
- Store in dry, cool and non-corrosive environment.
- While handling and processing, wear the personal protective equipment.
- Refer to the accompanying Material Safety Data Sheet (MSDS) for any specific emergency information.

SHELF LIFE

Following the previously named advices, the durability of this alloy when solid (without flux) is indefinite at room temperature. Consult the MSDS for additional precautions and procedures.

AVAILABLE FORMATS

Diameters from 0.5mm to 6mm.

Plastic reels of:

- 100 g.: 30 units/box
- 250 g.: 40 units/box
- 500 g.: 20 units/box
- 1 kg.: 10 units/box
- 2 kg and 4 kg: Under demand

** It can be supplied in:

- Round rods of 6x400 mm.
- Square rods of 4x9x400 mm.
- Rectangular rods of 12x24x400 mm.

Our recommendation is based on wide technical studies and a great practical experience. However, due to the wide variety of materials and working conditions in which our products are used, we do not assume any responsibility over the obtained result or caused damage due to misuse.

Revision date: 18/03/2020